



Ficha Técnica

**Sponge Natural Rubber
Property:**

Property	Test Method	Specification
Density (Average), lb./ft ³	ASTM D1056	26
Thickness, inches (Tolerance)	ASTM D1056	0.063-0.187 (+-0.015) 0.188 – 0.374 (+-0.030) 0.375 – 0.499 (+-0.040) 0.500 – 1.000 (+-0.060)
Standard Color, 3120	-	Black Tan
Polymer	-	Natural Rubber
Compression Deflection, psi	ASTM D1056 At 25% compression	5 - 10
Compression Deflection Change After Oven Aging, %	ASTM D1056 168hrs at 158°F (70°)	+20
Compression Set, % max.	ASTM D1056 50% deflection at 158° (70°C)	15
Temperature Range		-20°F to 160°F